

## PRODUCT DESCRIPTION

Perfection Undercoat is the ideal base for a long lasting scheme, when used with Perfection finish. The 2-component formulation has excellent obliteration.

\* Long overcoating times to allow coat-on-coat application

\* Easy application

Rubs down to an exceptionally smooth finish and the semi-gloss finish allows easy checking for hull fairness.

## PRODUCT INFORMATION

<b>Colour</b>	YRA003-White 001, YRA302-Blue 302, YRA603-Dark Grey 603
<b>Finish</b>	Semi-gloss
<b>Specific Gravity</b>	1.39
<b>Volume Solids</b>	50%
<b>Mix Ratio</b>	3:1 by volume , Converter/Curing Agent - YGA006
<b>Typical Shelf Life</b>	2 yrs
<b>VOC (As Supplied)</b>	488 g/lt
<b>Unit Size</b>	750 ml

## DRYING/OVERCOATING INFORMATION

	Drying			
	5°C	15°C	23°C	35°C
Touch Dry [ISO]	11hrs	7hrs	3hrs	2hrs
Sandable	48hrs	30hrs	16hrs	12hrs
Pot Life	5hrs	3hrs	2hrs	1hrs

Overcoated By	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Perfection	32hrs	4days	16hrs	3days	10hrs	2days	8hrs	1days
Perfection (Eu)	32hrs	4days	16hrs	3days	10hrs	2days	8hrs	1days
Perfection Undercoat	32hrs	4days	16hrs	3days	10hrs	2days	8hrs	1days

## APPLICATION AND USE

### Preparation

#### PREVIOUSLY PAINTED SURFACES:

**In Good Condition:** Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.

**In Poor Condition:** Remove all previous coatings and prime the substrate.

**PRIMING:** All preparation for bare substrates is covered on the appropriate primer datasheet.

**BARE WOOD:** Prime with UCP.

**STEEL:** Prime with Interprotect.

**ALUMINIUM:** Pre-prime using Etch Primer. Prime with Interprotect.

**GRP:** Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry. Abrade with 180-220 grade paper.

**ALL SUBSTRATES:** If any filling is required use the appropriate product from the Interfill range.

### Method

If maximum overcoating time of previous coating/primer is exceeded, abrade using 180-220

grade paper. Remove dust with a dust wipe. Apply 1-2 coats.

<b>Hints</b>	<b>Mixing</b> Stir contents of each part prior to mixing. Add Curing Agent to the Base, stir and leave for 10 minutes to allow bubbles to disperse. <b>Thinner</b> YTA006 Thinners No.9 <b>Cleaner</b> YTA006 Thinners No.9 <b>Ventilation and Humidity Control</b> Apply in dry, well ventilated conditions. Avoid excessively humid conditions, over 80% relative humidity. <b>Other</b> Best applied at 15°C. To give extra depth of colour, Perfection finish colours may be added to Perfection Undercoat. Both products should be mixed with respective curing agent first.
<b>Some Important Points</b>	Do not use unless mixed thoroughly with the curing agent at specified ratio. Product temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
<b>Compatibility/Substrates</b>	Will crack on carvel and clinker/lapstrake hulls. Perfection Undercoat should be applied over cured epoxy primers or fillers or onto cured GRP/Composite. It should not be used over any one pack products.
<b>Number of Coats</b>	1-2
<b>Coverage</b>	(Theoretical) - 12.00 (m <sup>2</sup> /lt)
<b>Recommended DFT</b>	38 microns dry by brush
<b>Recommended WFT</b>	75 microns wet by brush
<b>Application Methods</b>	Brush, Roller , DO NOT SPRAY

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<b>GENERAL INFORMATION:</b> Exposure to air and extremes of temperature should be avoided. For the full shelf life of Perfection Undercoat to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight. <b>TRANSPORTATION:</b> Perfection Undercoat should be kept in securely closed containers during transport and storage.
<b>Safety</b>	<b>GENERAL:</b> Contains isocyanates which may be harmful to the respiratory tract. Read the label safety section for Health and Safety Information, also available from our Technical Help Line. <b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of Perfection Undercoat cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

## DISCLAIMER

*The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

**X** and International are registered trademarks of Akzo Nobel.

## Regional Addresses

**Head Office**  
International Coatings Ltd  
P O Box 20980  
Oriel House  
16 Connaught Place  
London W2 2ZB  
United Kingdom  
tel: +44 (0) 171 479 6000  
fax: +44 (0) 171 479 6500

**European Region**  
International Coatings Ltd  
Stoneygate Lane  
Felling, Gateshead  
Tyne & Wear NE10 0JY  
United Kingdom  
tel: +44 (0) 191 469 6111  
fax: +44 (0) 191 438 3977

**Asia Region**  
International Coatings Pte Ltd  
449 Tagore Industrial Avenue  
01-03 Hong Joo Industrial  
Building  
Singapore 787820  
tel: +65 6453 1981  
fax: +65 6453 1778

**Australasia Region**  
Akzo Nobel Pty Limited  
115 Hyde Road  
Yeronga, Brisbane  
Queensland 4104  
Australia  
tel: +61 (0) 7 3892 8866  
fax: +61 (0) 7 3892 4287

**North America Region**  
International Paint Inc  
2270 Morris Avenue  
Union  
New Jersey 07083  
USA  
tel: +1 (0) 908 686 1300  
fax: +1 (0) 908 686 8545

**South America Region**  
Akzo Nobel Coatings Ltd  
Rod Rap tavares, KM 18.5  
Predio Administrativo 11  
Butanta CEP 05577-300  
Sao Paulo, Brazil  
tel: +55 (0) 11 3789 2000  
fax: +55 (0) 11 3789 2200



